

IDIV

GR 93

Constitution	emulsion of waxes and selected natural oil
Appearance	white creamy liquid
pH	7.8-8.5
Character	lightly anionic
Active substance	more than 40%

Method of use

GR 93 is a bottom coat with good sealing properties and dilutable in any proportion with water. Its use is advisable any time a good sealing of the leather is necessary for a good finishing process.

GR 93 can be employed for full grain leather and the quantity to be used is 100-150 grs/liter solution. Nevertheless its sealing capacity the finishing process is not effected and there is no adhesion problem for the next coat. The skin processed with **GR 93** maintain the grain smooth and flat.

GR 93 is perfectly glazeable and is suitable for the polish.

edition 07/2001

The information given herein is, to the best of our knowledge true and accurate. But it is given as a guidance only and is not to be taken as a warranty of results.