

IDIV

SYN FLR

Appearance	light brown paste
Active substance	35% app.
pH	7-8
Constitution	retanning auxiliary
Reaction	anionic

Method of use

SYN FLR has very good filling properties and therefore it is particularly suitable for skins requiring good fullness. A combination of **SYN RB** and **SYN FLR** gives the best result in the retanning of many articles from glazed for shoe upper to nappa for garment.

SYN FLR can be used together with fatliquoring or after but using the same bath. It doesn't interfere with dyeing. Advisable percentage is 4-5% on shaved weight dissolved in water at 50-60 °C.

Recipe

cow calf glazed
after dyeing and fixing:

Water 50°C	200%	
Fatliquoring	X%	
SYN FLR	3%	Run 60'
SYN RB	3%	Run 30', Drain
Water 30°C	200%	
SYN 04	3%	Run 30', Drain-Light Wash-Horse Up

Nappa for garment

Water 50°C	200%	
IDOIL NL	10%	
SYN FLR	4%	Run 60'
SYN SM	3%	Run 30'
IDOIL C/3	0.5%	Run 20'

The information given herein is, to the best of our knowledge true and accurate. But it is given as a guidance only and is not to be taken as a warranty of results.