

IDIV

WX SG

Constitution	wax emulsion
Appearance	white liquid
Solid content	18% app.
Character	anionic
pH	8-9

Method of use

WX SG is a chemical especially used to upgrade full chrome leather of bad quality. Thanks to its characteristics it can be employed on heavily buffed leather through a roll coating machine application. After drying the skin shows a white surface and it is ready to be brushed to obtain a remarkable burnish.

WX SG can be employed with success also on full grain leather to obtain a perfect sealing and an excellent uniformity of absorptions.

WX SG can be used also with **WX 105** to obtain different articles.

An EXAMPLE of application for a reactive burnish is the following:

Buffing paper 240-400

WX 105 500
WX SG 300
WATER 500
UR 84 100 1 roll coat grs/sqft 8-9, tunnel 50°C; rest 4 hours

WX 105 500
WATER 1200
WX SG 300
UR 84 100 2 crosses, staking well

The information given herein is, to the best of our knowledge true and accurate. But it is given as a guidance only and is not to be taken as a warranty of results.